

polytec High Pressure Laminate

General Information

polytec's range of Laminate and Benchtops are designed for applications such as kitchen worktops, countertops, bathroom vanities and laundry benchtops where a durable decorative surface is required.

Features

- Tough and durable
- Resistant to cracking, chipping, chemicals and reagents
- Industry relevant colour range

Environmental/Safety

polytec is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health and environmental protection. We support the safe handling of our products.

PHYSICAL PROPERTIES	TYPICAL PROPERTY	TEST METHOD
Density (kg/k ³)	1350 - 1450	DIN 53479
Panel Tolerance (mm)		
Length	+/- 5	DIN 16926
Width	+/- 5	
Thickness	+/- 0.1	
Colour Stability	Blue wool standard Min 6	AS/NZS 2924.1
Thickness Swell (24hr @ 20°C)	3.5%	EN 317
Tensile Strength (N/mm ²)	>80	DIN 53457
Flexural Strength (N/mm ²)	>90	DIN 53457
Resistance to Impact (N)	>20	AS/NZS 2924.1
Resistance to Scratch	e 2	AS/NZS 2924.1
Resistance to Wear	e 350	AS/NZS 2924.1
Resistance to Steam	e 4	AS/NZS 2924.1
Dry Heat Resistance, 180°C		
Finishes	e 4	AS/NZS 2924.1
Resistance to Staining		
Group 1 + 2	e 5	AS/NZS 2924.1
Group 3 + 4	e 4	
Resistance to Boiling Water	No Visible Change	AS/NZS 2924.1

Fire Hazard Indices		
Ignitability Index	10 - 14	AS/NZS 1530.3
Spread of Flame Index	0 - 8	
Heat Evolved Index	2 - 6	
Smoke Development Index	2 - 4	

Chemical Resistance Test Results

polytec always recommend prompt clean-up of all spills on its decorative surfaces and the surface maintained in accordance with our Care and Maintenance instructions.

Performance	Chemical
No visible effect	Water, alcohol 96%, isopropanol, Petrol, amy1 acetate, acetone, household soap, detergents for dishwashing by hand, ammonium hydrate 10%, ketchup, cooking oil, trisodium phosphate 1%, coffee, tea, milk, acetic acid, caustic soda (<10%), citric acid 10%, wine, lipstick, grapefruit juice, wax, shoe polish, ink ballpoint pen, spirit dye pen, marking ink, hand cream
Slight Effect/No Effect if completely removed within 10-15 minutes	Hydrogen Peroxide 30%, hypochlorite bleach, hair dye, mercury chromate 2%, iodine, hydrochloric acid (<10%), phosphoric acid (10%), caustic soda (>10%)
Surface attack/necessitating immediate removal	Hydrochloric Acid (>10%, nitric acid (>10%), Sulphuric Acid (>10%)

Contact

For further information on this product, please contact the following:

Polytec Laminates, No. 1, Jalan Teknologi Utama PLO2, Kawasan Perindustrian Mengkibol, 86000 Kluang, Johor, Malaysia Telephone: +60 (7) 776 2600 Fax: +60 (7) 776 2608

Whilst the information contained in this document is based on data, which, to the best of our knowledge, was accurate and reliable at the time of preparation, we can accept no responsibility for errors and omissions. The provision of this information should not be construed as a recommendation to use any of our products in violation of any patent rights or breach of any statute or regulation. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, we can accept no responsibility for any loss or damage caused by any person acting or refraining from action as a result of this information.

Date of last update: 1 August 2016